

NIPPON ROOF COATING

External Emulsion

Product Description:

Nippon Roof Coating is an acrylic paint which is specially formulated for painting and repainting of asbestos and tiles roof. It is easy to apply and forms a smooth thorough film which is durable, fungus resistant, and has excellent gloss and low dirt collection.

Recommended Uses:

For decoration and protection of asbestos and tiles roof surface.

Composition:

Pigments : Mainly Tio₂, Iron Oxide, Carbon Black, etc.
Binder : All Acrylic Emulsion
Thinner : Water

Properties:

Colour : Wide range of colour. Please refer colour card.
Appearance : High Gloss

Recommended no. of coats : 2 - 3 coats

Recommended Dry Film Thickness Per Coat : 35 - 50 µm

Drying Time

Touch Dry : Minimum 30 minutes
 Hard Dry : Minimum 3 hours

Recoating Interval : Minimum 4 hours

Theoretical Coverage at Recommended Dry Film Thickness : 11 - 12 m² per litre per coat
 (Actual coverage is dependent on substrate condition.) *

Application Methods:

1) Brush / Roller : This paint is ready for use after thorough stirring. If necessary, thin with 5% water.

2) Conventional Air Spray : Dilute with 10% water.

3) Airless Spray : Dilute both the 1st and 2nd coats with 5% water.

Clean Up : Clean up equipment with water immediately after use.

Surface Preparation:

Remove all dirt by water jetting. Allow surfaces to dry out thoroughly. Ensure that the surfaces are free from loose dirt, dust, grease, oil and other contaminants. All unstable paint film must also be removed.

Previously Painted Surfaces

Remove all unstable paint film, loose chalk, dust, fungus / algae and foreign matter. Make good any surface defects, clean off and dry.

Recommended Paint System**Type of Substrate:**

FOR ASBESTOS AND TILES

Sequence	Product Name	No. of Coats
Finish	NIPPON ROOF COATING	2 - 3

Standard Packing : 5 litres

Safety, Health and Environmental Information:

Keep container tightly closed and keep out of reach of children or away from food and drink.
 Ensure good ventilation during application and drying.
 When applying paint, it is advisable to wear eye protection.
 In case of contact with eye, rinse with plenty of water immediately and seek medical advice.
 Remove splashes from skin by using soap or water.
 Paint must always be stored in a cool place.
 When transporting paint, care must be taken. Always keep container in a secure upright position.
 Dispose off any paint waste in accordance with the appropriate Environmental Quality Regulations.

Note:

* Theoretical Coverage is based on a mathematical formula

$$\left[\frac{\text{Volume Solid \% x 10}}{\text{Dry Film Thickness}} \right] = \text{m}^2 / \text{lit} / \text{coat}$$

and does not consider LOSS FACTORS.

Variables like porosity of substrate, application method, dilution ratio, dry film thickness, opacity and so on will affect the loss factor and can vary from 30% - 50% or even more.

The above information is given to the best of our knowledge based on laboratory tests and practical experience. However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself.

We reserve the right to alter the given data without prior notice.