

## **NIPPON SATIN GLO**

### *Internal Emulsion*

**Product Description:**

Nippon Satin Glo is an acrylic-based paint with non-added lead and mercury which gives a luxury wall finish. It is a durable decorative finish specially formulated to provide a smooth mid sheen finish. It is washable and fungus resistant.

**Recommended Uses:**

For the decoration and protection of interior walls.

**Composition:**

<b>Pigments</b>	:	Mainly Titanium Dioxide, Iron Oxide, Carbon Black and Organic Pigments and Mineral Extender
<b>Binder</b>	:	All Acrylic
<b>Thinner</b>	:	Water

**Properties:**

<b>Colour</b>	:	A wide range of colours. Please refer to colour card.
<b>Appearance</b>	:	Mid Sheen

<b>Recommended no. of coats</b>	:	2 coats
<b>Recommended Dry Film Thickness Per Coat</b>	:	30 - 40 $\mu$ m
<b>Drying Time</b>		
Touch Dry	:	Dependent on temperature and humidity.
Hard Dry	:	3 – 4 hours
<b>Recoating Interval</b>	:	4 hours
<b>Theoretical Coverage at Recommended Dry Film Thickness</b>	:	10 - 12 m <sup>2</sup> per litre per coat (Actual coverage is dependent on substrate condition.) *

**Application Methods:**

<b>1) Brush / Roller</b>	:	For the 1 <sup>st</sup> and 2 <sup>nd</sup> coats, dilute with 5% water
<b>2) Conventional Air Spray</b>	:	Dilute the paint with 20-25% water
<b>3) Airless Spray</b>	:	Dilute the paint with 5% water for the 1 <sup>st</sup> and 2 <sup>nd</sup> coats.
<b>Clean Up</b>	:	Clean up equipment with water immediately after use.

**Surface Preparation:**

Remove all loose, defective paint or powdery residues. Repair cracks, uneven surfaces with Nippon ACS Putty or suitable fillers. Smoothen the putty / filler areas with sandpaper. Surfaces to be painted must be cleaned thoroughly and dry, it must be free from dirt, grease and other foreign matters. Allow all surfaces to dry completely prior to painting. Avoid painting when the moisture content and alkalinity of the walls is still high. (Recommended painting specification requires the moisture content of the walls to be below 16% measured by protimeter and alkalinity of the wall to be below pH9.)

**Previously Painted Surfaces**

Remove all unstable paint film, loose chalk, dust and foreign matter. Make good any surface defects, clean off and dry. Spot prime with NIPPON VINILEX 5200 WALL SEALER.

**Recommended Paint System****Type of Substrate:**

FOR MASONRY

Sequence	Product Name	No. of Coats
Sealer	NIPPON VINILEX 5200 WALL SEALER / NIPPON ACRYLIC 5170 WALL SEALER / NIPPON HI-BOND WALL SEALER	1
Finish	NIPPON SATIN GLO	2

**Standard Packing** : 5 litres

**Safety, Health and Environmental Information**

Keep container tightly closed and keep out of reach of children or away from food and drink.

Ensure good ventilation during application and drying.

When applying paint, it is advisable to wear eye protection.

In case of contact with eye, rinse with plenty of water immediately and seek medical advice.

Remove splashes from skin by using soap or water.

Paint must always be stored in a cool place.

When transporting paint, care must be taken. Always keep container in a secure upright position.

Dispose off any paint waste in accordance with the appropriate Environmental Quality Regulations.

**Note:**

\* Theoretical Coverage is based on a mathematical formula

$$\left[ \frac{\text{Volume Solid \%} \times 10}{\text{Dry Film Thickness}} \right] = \text{m}^2 / \text{lit} / \text{coat}$$

and does not consider LOSS FACTORS.

Variables like porosity of substrate, application method, dilution ratio, dry film thickness, opacity and so on will affect the loss factor and can vary from 30% - 50% or even more.

The above information is given to the best of our knowledge based on laboratory tests and practical experience.

However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself.

We reserve the right to alter the given data without prior notice.