

MICACEOUS IRON OXIDE
Updated Aug'16


Micaceous Iron Oxide is an alkyd based coating pigmented with micaceous iron oxide. It is recommended for use as protective coating on steel structures. It may be overcoated with alkyd based finish or left uncoated.

Product Features:

- Chemical resistant
- Weather resistant

Paint Type	Product Type	Finishing	Recommended Substrate	Pack Size
Solvent based	Interior & Exterior	Low Gloss	Wood and Metal	5 Litres, 20 Litres

Composition

Pigment	: Aluminium and Extender
Binder	: Alkyd
Thinner	: General Purpose Thinner

Technical Data

Drying Time	: Touch Dry	: 1 hour
	: Hard Dry	: 16 hours
Recoating Interval	: Minimum 16 hours	
Dry Fil Thickness	: 50 - 60 µm per coat (dry film thickness)	
No. of Coats	: 1 - 2 coats	
Theoretical Coverage	: 10.2 m ² per litre (for dry film thickness of 50um)	
	: 8.5 m ² per litre (for dry film thickness of 60um)	
Practical Coverage (20% Loss Factor)	: 8.2 m ² per litre (for dry film thickness of 50um)	
	: 6.8 m ² per litre (for dry film thickness of 60um)	
Volume Solid	: ~ 51% by volume	
Shelf Life	: Up to 24 months in tight sealed container	

Application Method

Brush/ Roller	: If necessary, add up to 5% thinner by volume.	
Compressed Air Spray	: If necessary, add up to 15% thinner by volume.	
Airless Spray	: Delivery pressure	: 140 – 170 kg/cm ²
	: Tip size	: 0.015" – 0.017"
	: Spray angle	: 60° - 70°
	: Dilution	: Up to 5% thinner by volume

Recommended Coating System

Sealer / Primer	: Not applicable	
Top Coat	: Micaceous Iron Oxide	: 2 coats

Surface Preparation

The surface must be free from millscale, rust, grease, oil and other contaminants; it must be dry at the time of application.

Cleaning

Clean up equipment with thinner immediately after use.

Safety Precautions

- Do not apply when the relative humidity exceeds 85% or when the surface to be coated is less than 3°C above the dew point.
- Do not apply at temperature below 7°C. If not, drying and overcoating times will be considerably extended.
- Keep container tightly closed and keep out of reach children or away from food and drink.
- Ensure good Ventilation during application and drying.
- During application of paint, naked flames, welding operation, and smoking should not be allowed.
- When applying paint, it is advisable to wear eye protection.
- In case of contact with eye, rinse with plenty of water immediately and seek medical advice.
- Remove splashes from skin by using soap or water.
- Paint must always be stored in a cool place.
- When transporting paint, care must be taken. Always keep container in a secure upright position.
- Dispose off any paint waste in accordance with the appropriate Environment Quality Regulations.

Note

* Theoretical Coverage is based on a mathematical formula

$$\left[\frac{\text{Volume Solid \%} \times 10}{\text{Dry Film Thickness}} \right] = \text{m}^2/\text{lit}/\text{coat}$$

Note: This theoretical coverage rate has been calculated from the volume solids of the material and is related to the amount of coating applied onto a perfectly smooth surface without wastage. For a practical coverage rate, due allowance should be made for atmospheric conditions, surface roughness, geometry or the article being coated, the skill of applicator etc. when estimating quantities required for a particular job.

The above information is given to the best of our knowledge based on laboratory tests and practical experience.

However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself.

We reserve the right to alter the given without prior notice