

**Q-SHIELD EXTRA**
*Updated Aug'18*


Q-Shield Extra is a waterborne acrylic based emulsion paint with non-added lead and mercury specially formulated for exterior walls. It provide good inter-adhesion between substrate and topcoat with low dirt retention properties.

**Product Features:**

- Chalking and flaking resistance
- Non-toxic, does not contain lead, mercury and heavy metals
- Good exterior durability against harsh weather
- Fungus and algae resistance
- Approved by SIRIM to Malaysian Standard MS 134:2007

Paint Type	Product Type	Finishing	Recommended Substrate	Pack Size
Water based	Exterior	Low Sheen	Masonry, brick, plastering substrate and fibre board	1 Litre, 5 Litres, 20 Litres

**Composition**

Pigment	: Mainly Titanium Dioxide, Iron Oxide, Carbon Black and Organic Pigments and Mineral Extender
Binder	: Pure Acrylic Emulsion
Thinner	: Water

**Technical Data**

Drying Time	: Touch Dry : 20 minutes (Dependent on temperature and humidity)
	: Hard Dry : 1 hour (Dependent on temperature and humidity)
Recoating Time	: 2 (Dependent on temperature and humidity)
Dry Film Thickness	: Around 30 µm per coat (based on substrate condition)
No. of Coats	: 2 coats
Theoretical Coverage	: 10 – 12 m <sup>2</sup> per litre per coat (Actual coverage is dependent on substrate condition, application method, application condition and finishing appearance)
Volume Solid	: ~ 38%
Shelf Life	: Up to 36 months in tight sealed container

**Application Method**

Brush / Roller	: Dilute the paint with not more than 5% of water. Preferable not dilute for best performance.
----------------	--

**Recommended Coating System**

Sealer / Primer	: Vinilex 5100 Wall Sealer / Advance 8000 Wall Sealer / Expresskote Sealer / Acrylic 5170 Wall Sealer / Hi-Bond Wall Sealer (on powdery or skim-coated surface)	: 1 Coat
Top Coat	: Q-Shield Extra	: 2 Coats

**Surface Preparation**

Remove all loose, defective paint or powdery residues, loose chalk, dust, fungus, algae and foreign matter. Treat any areas affected by fungus growth with Fungicidal Wash Solution. Repair cracks, uneven surfaces with suitable exterior grade fillers. Smoothen the filler areas with sand paper. Surfaces to be painted must be cleaned thoroughly and dry, it must be free from dirt, grease and other foreign matters. Allow all surfaces to dry completely prior to painting. Avoid painting when the moisture content and alkalinity of the walls are still high. (Recommended painting specification requires the moisture content of the walls to be below 16% measured by protimeter and alkalinity of the walls to be below pH9.) Spot prime with Nippon Exterior Wall Sealer.

**Cleaning**

Clean up equipment with water immediately after use.

**Safety Precautions**

- Keep container tightly closed and keep out of reach children or away from food and drink.
- Ensure good Ventilation during application and drying.
- When applying paint, it is advisable to wear eye protection.
- In case of contact with eye, rinse with plenty of water immediately and seek medical advice.
- Remove splashes from skin by using soap or water.
- Paint must always be stored in a cool place.
- When transporting paint, care must be taken. Always keep container in a secure upright position.
- Dispose off any paint waste in accordance with the appropriate Environment Quality Regulations.

**Note**

\* Theoretical Coverage is based on a mathematical formula

$$\left[ \frac{\text{Volume Solid \%} \times 10}{\text{Dry Film Thickness}} \right] = \text{m}^2/\text{lit}/\text{coat}$$

and does not consider LOSS FACTORS.

Variables like porosity of substrate, application method, dilution ratio, dry film thickness, opacity and so on will affect the loss factor and can vary from 30% - 50% or even more.

The above information is given to the best of our knowledge based on laboratory tests and practical experience.

However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself.

We reserve the right to alter the given without prior notice.